



US005367044A

**United States Patent** [19]**Rosenquist**[11] **Patent Number:** **5,367,044**[45] **Date of Patent:** **Nov. 22, 1994**

[54] **BLOW MOLDED ARTICLE MOLDED FROM  
A COMPOSITION COMPRISING A  
RANDOMLY BRANCHED AROMATIC  
POLYMER**

[75] **Inventor:** Niles R. Rosenquist, Evansville, Ind.

[73] **Assignee:** General Electric Company, Pittsfield,  
Mass.

[21] **Appl. No.:** 928,075

[22] **Filed:** Aug. 12, 1992

**Related U.S. Application Data**

[63] Continuation of Ser. No. 596,186, Oct. 12, 1990, abandoned.

[51] **Int. Cl.<sup>5</sup>** ..... C08G 64/00

[52] **U.S. Cl.** ..... 528/204; 528/196

[58] **Field of Search** ..... 528/204, 196

[56] **References Cited**

**U.S. PATENT DOCUMENTS**

4,695,620 9/1987 Masumoto et al. .... 528/204

4,888,400 12/1989 Boden et al. .... 528/204

*Primary Examiner*—John Kight, III

*Assistant Examiner*—T. Mosley

[57] **ABSTRACT**

A composition comprising a randomly branched aromatic polycarbonate polymer wherein the branching agent 1,1,1-tris-(4-hydroxyphenyl)ethane is present in the polymer in quantities ranging from about 0.28 to about 0.36 mole percent compound based on the percent of dihydric phenol present in the polymer.

**4 Claims, No Drawings**